

Data sheet Issue 11/22

### **DEX-125**

**Epoxy hardener DEX-125** 

#### **Product data**

#### **Decription**

DEX-125 curing agent is a medium viscosity, reactive polyamide based on dimerized fatty acid and polyamines designed for use with solid or liquid epoxy resins for tough, chemical-resistant thermoset coating applications that cure at room temperature. This resin is also useful in adhesive applications. It has very good performance of excellent chemical resistance and excellent adhesion.

#### **Packing**

- NET WEIGHT 190KG DRUM

## **Technical Properties**

Property	Unit	Value
Color	GARDNER	MAX9
Viscosity	MPA.S AT 40°C	8000-12000
Amine value	MG KOH/G	290-310
A.H.E.W	G/EQ	102
Recommended use level	PHR, EEW=190	50-60
Gel time	MINUTES, 25°C,100G	30-40

# **Applications**

DEX-125 can be widely used in maintenance coating applications, primers and enamel paint formulations.

#### © DEXRESIN

China Jiangsu, Changzhou Tel +86 0512 63659101

sales@dexresin.com info@dexresin.com

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.